

Claims

1. A method of producing a fibre reinforced composite by pultrusion having variable strength characteristics along its length including the steps of drawing through a pultrusion die a series of reinforcing fibres to form a pultruded fibre composite product characterised by incorporating in the reinforcing fibres prior to the pultrusion step additional fibres having a characteristic different from that of the said reinforcing fibres in order to vary the strength characteristics of the final product substantially without altering the cross-sectional area thereof, a plastics matrix material being applied around the fibres and allowed to solidify to form the finished composite.
2. A method according to claim 1 in which the said characteristic is selected from the group fibre tenacity and fibre modulus.
3. A method according to claim 1 or 2 in which the additional fibres are spliced between discrete lengths of the reinforcing fibres.
4. A method according to claim 1 or 2 in which the additional fibres are interlaced amongst continuous said reinforcing fibres.
5. A method according to any of claims 1 to 4 in which the plastics matrix material is applied to the fibres, within the die.
6. A method according to any of claims 1 to 4 in which the fibres are pre-impregnated with a plastics matrix material before being drawn through the die.
7. A method according to any preceding claim in which the fibres are in the form of a woven web.
8. A method according to any one of claims 1 - 6 in which the fibres are in the form of a non-woven web.

11. An aircraft aerofoil incorporating a composite structural member according to claim 9 or 10.

[illegible]